

**ELDON JAMES**

**EJ Prene™**

CHEMICAL RESISTANCE OF EJ Prene™ MATERIAL

## RESISTANCE RATINGS

Excellent	E	Good	G	Formal	F	Not Recommended	X	Not Tested	-
-----------	---	------	---	--------	---	-----------------	---	------------	---

CHEMICAL	RATING
Acetaldehyde	E
Acetic Acid, 10%	E
Acetic Acid, 50%	E
Acetic Acid, Glacial	E
Acetic Anhydride	E
Acetic Oxide	E
Acetone	E
Acetone Cyanohydrin	E
Acetonitrile	E
Acetophenone	G
Acetyl Acetone	E
Acetyl Chloride	X
Acetyl Oxide	E
Acetylene	E
Acetylene DI + Tetra Chloride	X
Acrolein	E
Acrylonitrile	X
Acrylic Acid	E
Air +300F	X
Alk-Tri	-
Allyl Alcohol	E
Allyl Bromide	F
Allyl Chloride	F
Alum	E
Aluminum Acetate	E
Aluminum Chloride	E
Aluminum Flouride	E
Aluminum Formate	E
Aluminum Hydroxide	E
Aluminum Nitrate	E
Aluminum Sulfate	E
Alums-NH3 CR K	E
Amines - Mixed	G
Aminobenzene	E
Aminodimethylbenzene	F
Aminoethane	E
Aminoxilene	F
Ammonium Carbonate	E
Ammonium Chloride	E
Ammonium Hydroxide	E
Ammonium Nitrate	E
Ammonium Phosphate, Dibasic	E

CHEMICAL	RATING
Ammonium Sulphate	E
Ammonium Sulphite	E
Ammonium Thiosulfate	E
Amyl Acetate	X
Amyl Acetone	F
Amyl Alcohol	E
Amyl Bromide	F
Amyl Chloride	X
Amyl Ether	F
Amylamine	F
Anethole	C
Aniline	E
Aniline Dyes	E
Aniline Oil	G
Animal Fats	G
Antmony Pentachloride	E
Aqua Regia	F
Argon	E
Arsenic Acid	E
Asphalt	F
ASTM Fuel A	F
ASTM Fuel B	C
ASTM Fuel C	C
ASTM Oil No. 1	F
ASTM Oil No. 2	X
ASTM Oil No. 3	X
ASTM Oil No. 4	X
Automatic Transmission Fluid	X
Banana Oil	G
Barium Chloride	E
Barium Hydroxide	E
Barium Sulfide	E
Beer	E
Beet Sugar Liquors	E
Benzel Chloride	C
Benzaldehyde	G
Benzene	X
Benzene Carboxylic Acid	E
Benzine	X
Benzoic Acid	E
Benzol	X
Benzotrichloride	X

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Benzyl Acetate	F
Benzyl Alcohol	F
Benzyl Chloride	F
Benzyl Ether	X
Bis (2-Chloroethyl) Ether	C
Black Sulfate Liquor	E
Bleach	G
Borax Solution	E
Boric Acid	E
Brake Fluid (HD-557) 12 Days	F
Brine	E
Bromacil	-
Bromobenzene	X
Bromochlorometane	F
Bromomethane	F
Bromotoluene	X
Bugdioxine	-
Bunker Oil	-
Butaoiene	C
Butane	C
Butanoic Acid	E
Butanol (Butyl Alcohol)	E
Butanone	E
Butoxyethanol	E
Butyl Acetate	X
Butyl Acrylate	X
Butyl Alcohol	E
Butyl Aldehyde	E
Butyl Bezy l Phthalate	G
Butyl Carbitol	C
Butyl Cellusolve	E
Butyl Chloride	G
Butyl Ether	G
Butyl Ether Acetaldehyde	G
Butal Ethyl Ether	F
Butyl Oleate	G
Butyl Phthalate	G
Butyl Stearate	G
Butylene	F
Butyraldehyde	E
Butyric Acid	E
Butyric Anhydride	E

CHEMICAL	RATING
Cadmium Acetate	E
Calcium Acetate	E
Calcium Aluminate	E
Calcium Bichromate	E
Calcium Bisulfide	C
Calcium Chloride	E
Calcium Hydroxide	E
Calcium Hypochlorite	G
Calcium Nitrate	E
Calcium Sulfide	E
Caprylic Acid	G
Carbamide	E
Carbitol	E
Carbolic Acid Phenol	F
Carbon Dioxide	E
Carbon Disulfide	X
Carbon Monoxide	E
Carbon Tetrachloride	X
Carbonic Acid	E
Castrol Oil	G
Caustic Sode (See Sodium Hydroxide)	E
Cellosolve Acetate	E
Cellugard	-
Cetylic Acid	G
China Wood Oil (Tung Oil)	-
Chlorinated Solvents	X
Chloro-2-Propane	F
Chloroacetic Acid	X
Chloroacetone	G
Chlorobenzene	X
Chlorobutane	G
Chlorodane	G
Chloroethyl Benzene	X
Chloroform	X
Chloropentane	F
Chlorosulfonic Acid	G
Chlorotoluene	F
Chlorox	G
Chrome Plating Solutions	E
Chromic Acid	G
Chromium Trioxide	G
Cinnamene	-

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Cis-9-Octadecenoic Acid	G
Citric Acid	E
Coal Oil	X
Coal Tar	F
Coal Tar Naphtha	F
Coconut Oil	G
Coke Oven Gas	F
Coolanol (Monsanto)	X
Copper Chloride	C
Copper Cyanide	C
Copper Hydrate	C
Copper Hydroxide	C
Copper Sulfate	C
Corn Oil	G
Cottonseed Oil	G
Creosote	G
Cresols	G
Cresylic Acid	G
Crotonaldehyde	E
Crude Oil	C
Cumene	X
Cupric Carbonate	E
Cupric Hydroxide	E
Cupric Nitrate	E
Cupric Sulfate	E
Cutting Oil	C
Cyclohexane	X
Cyclohexanol	G
Cyclohexanone	G
Cyclopentane	C
Cyclopentanol	G
Cyclopentanone	G
Cyclopentil Alcohol	G
D-Furaldehyde	G
DDT in Kerosene	X
Decahydronaphthalene	X
Decahydroxaphthalene	X
Decalin	X
Decyl Alcohol	G
Decyl Aldehyde	G
Decyl Butyl Phthalate	F
Decyl Carbinol	F

CHEMICAL	RATING
Detergent, Water Solution	E
Developing Fluid (Photo)	G
Dextron	E
Di (2ethylhexyl) Adipate	G
Di (2ethylhexyl) Phthalate	F
Di-Iso-Butylene	X
Di-Iso-Decyl Phthalate	G
Di-Iso-Propanolamine	G
Di-Iso-Propyl Ether	F
Di-Iso-Propyl Ketone	F
Di-P-Mentha-1, 8 Diene	X
Diacetone Alcohol	E
Diacetylmethane	G
Diallylphthalate	G
Diammonium Phosphate	E
Diamyl Naphthalene	X
Diamylamine	G
Diamylene	F
Diamylphenol	F
Dibenzyl Ether	F
Dibromobenzene	X
Dibromomethane	-
Dibutyl Ether	G
Dibutyl Phthalate	G
Dibutyl Sebacate	G
Dibutylamine	G
Dicalcium Phosphate	E
Dichloroethylene	F
Dichloroacetic Acid	E
Dichlorobenzene	F
Dichlorobutane	F
Dichlorodifluoromethane	X
Dichloroethane	F
Dichloroethyl Ether	F
Dichlorohexane	F
Dichloromethane	F
Dichloropentane	F
Dichloropropane	F
Dichloropropene	F
Dichlorotoluene	F
Diesel Oil	F
Diethanol Amine	G

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Diethyl Ether	G
Diethyl Ketone	G
Diethyl Oxalate	G
Diethyl Phthalate	G
Diethyl Sebacate	G
Diethyl Sulfate	E
Diethylamine	E
Diethylbenzene	X
Diethylene Glycol	E
Diethylene Oxide	E
Diethylenetriamine	E
Diethytriamine	E
Dihydroxy Diethyl Ether	E
Dihydroxy Succinic Acid	E
Dihydroxydiethyl Ether	E
Diisobutyl Ketone	F
Diisodecyl Phthalate	F
Diisooctyl Adipate	F
Diisooctyl Phthalate	F
Dimethyl Carbinol	E
Dimethyl Ketone	G
Dimethyl Phthalate	G
Dimethyl Sulfate	G
Dimethyl Sulfide	G
Dimethyl-3-Pentanone	F
Dimethyl-4-Heptanone	F
Dimethylamine	E
Dimethylaniline	G
Dimethylbenzene	X
Dimethylbutane	C
Diocetyl Adipate	F
Diocetyl Phthalate	G
Dioxalane	G
Dioxane	G
Dipentene	F
Dipentylamine	F
Diproylamineolamine	G
Dipropylene Glycol	E
Disodium Phosphate	E
Divinyl Benzene	X
Dowell Inhibitor	-
Dowfax 2A1 Solvent	-

CHEMICAL	RATING
Dowfax 2A1 TA	-
Dowfax 6A1 Solvent	-
Dowfax 6A1 TA	-
Dowthermn, A and E	-
Dry Cleaning Fluids	X
Ducgkirioebaane	-
Duro AW-16, 31	-
Duro FR-HD	-
Ethanoic Acid	E
Ethanol (Grain Alcohol)	-
Ethanolamine	E
Ethers	G
Ethyl Acetate	E
Ethyl Acetoacetate	E
Ethyl Acetone	E
Ethyl Acrylate	E
Ethyl Alcohol	E
Ethyl Aldehyde	E
Ethyl Aluminium Dichloride	E
Ethyl Benzene	X
Ethyl Bromide	F
Ethyl Butyl Acetate	-
Ethyl Butyl Alcohol	-
Ethyl Cellulose	E
Ethyl Chloride	F
Ethyl Di-isobutylthio-Carbamate	E
Ethyl Dichloride	X
Ethyl Ether	G
Ethyl Formate	E
Ethyl Iodide	G
Ethyl Oxalate	E
Ethyl Phthalate	G
Ethyl Silicate	E
Ethyl-1-Butanol	G
Ethyl-N-Butyl Ketone	G
Ethylamine	G
Ethylene Chlorohydrin	E
Ethylene Diamine	E
Ethylene Dibromide	C
Ethylene Dichloride	C
Ethylene G Monobutyl Ether	G
Ethylene G Monoehexil Ether	G

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Ethylene G Monoethyl E Acetate	G
Ethylene G Monoethyl Ether	-
Ethylene Glycol	E
Ethylene Oxide	E
Fatty Acids	G
Ferric Bromade	E
Ferric Chloride	E
Ferric Nitrate	E
Ferric Sulfate	E
Ferrous Acetate	E
Ferrous Chloride	E
Ferrous Sulfate	E
Fluoboric Acid	E
Fluorine	X
Fluosilicic Acid	E
Formaldehyde	E
Formalin	E
Formic Acid	E
Freon 113	X
Freon 12	X
Freon 22	X
Freon so2	X
Fuel A (ASTM)	F
Fuel B (ASTM)	C
Fuel Oil	X
Furan	F
Furfural	G
Furfuran	F
Furfuryl Alcohol	G
Gallic Acid	G
Gallotanic Acid	-
Gas, Coal	C
Gas, High Octane	C
Gasoline	X
Glacial Acrylic Acid	E
Gluconic Acid	E
Glucose	E
Glycerine	E
Glycerol	E
Glycogenic Acid	G
Glycols	E
Glyconic Acid	E

CHEMICAL	RATING
Glycyl Alcohol	E
Grease	F
Green Sulphate Liquor	E
Halon 1211	-
Helium	E
Heptaldehyde	G
Heptanal	G
Heptane	X
Heptane Carboxylic Acid	G
Heptanoic Acid	G
Heptanone	F
Hexadecanoic Acid	F
Hexaldehyde	G
Hexane	X
Hexanol	G
Hexene	C
Hexyl Alcohol	G
Hexyl Methyl Ketone	F
Hexilamine	G
Hexylene Glycol	E
Histowax	-
Hydraulic Motor Oil	C
Hydrazine	E
Hydrobromic Acid	E
Hydrocyanic Acid	E
Hydrochloric Acid	E
Hydroflouric Acid	X
Hydrogen Chloride Anhydrous	E
Hydrogen Dioxide (10%)	-
Hydrogen Gas	E
Hydrogen Peroxide 10%	G
Hydrogen Peroxide over 10%	F
Hydrogen Sulfide (wet)	E
Hydroxy Benzene	F
Hydroxyisobutyronirile	E
Hydroxytoluene	F
Hyvar XL	-
Iminodi-1-Propanol	G
Iminodiethanol	G
Iodine	E
Iodine Pentafluoride	X
Iodoform	G

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Iso-Butanal	G
Iso-Butylamine	G
Iso-Butylbromide	F
Isobutylcarbinol	G
Iso-Octane	X
Isocyanates	G
Isooctane	X
Isopropyl Acetate	-
Isopropyl Alcohol	E
Isopropyl Ether	F
Jet Fuels	X
Jp-4 Oil	X
Kerosene	X
Ketones	C
Lacquer Solvents	X
Lactic Acid - Cold	E
Lactic Acid - Hot	E
Lard	G
Lavender Oil	F
Lead Acetate	-
Lead Nitrate	E
Lead Sulfate	E
Lime	E
Lime Bleach	E
Lime Sulfur	E
Limonene	X
Linoleic Acid	F
Linseed Oil	F
Liquid Petroleum Gas (LPG)	X
Lubricating Oils	X
Lye Solutions	G
Magnesium Acetate	E
Magnesium Chloride	E
Magnesium Hydrate	E
Magnesium Hydroxide	E
Magnesium Sulfate & Sulphite	E
Maleic Acide	E
Maleic Anhydride	E
Malic Acid	E
Manganous Sulfate	E
Mapp	G
Mek	E

CHEMICAL	RATING
Mercury	E
Mercury Vapours	E
Mesityl Oxide	F
Methallyl Chloride	G
Methane Carboxylic Acid	E
Methanoic Acid	E
Methanol (Methyl Alcohol)	E
Methanol (Wood Alcohol)	E
Methoxy Ethanol	E
Methoxyethoxy Ethanol	E
Methoxypropenyl Benzene	F
Methyl 1-2, 4-Pentanediol	E
Methyl Acetate	E
Methyl Acetoacetate	E
Methyl Acetone	G
Methyl Acetylene Propadiene	C
Methyl Alcohol	E
Methyl Allyl Alcohol	E
Methyl Allyl Chloride	G
Methyl Amyl Carbinol	G
Methyl Benzene	X
Methyl Bromide	C
Methyl Butane	C
Methyl Butyl Alcohol	G
Methyl Butyl Ketone	G
Methyl Carbitol	-
Methyl Cellosolve	E
Methyl Chloride	G
Methyl Cyanide	E
Methyl Ethil Ketone	E
Methyl Hexanol	G
Methyl Methacrylate	G
Methyl Normal Amyl Ketone	F
Methyl Propyl Ether	G
Methyl Salicylate	G
Methyl Styrene	X
Methyl Sulfide	G
Methyl Tertiary Butyl Ether	F
Methyl-2-Butanol	G
Methyl-2-Butanone	G
Methyl-2-Hexanone	F
Methyl-2-Pentanol	G

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING	CHEMICAL	RATING
Methyl-2-Pentanone	F	Mil-J-5624 (Jp-3, Jp-4, Jp-5)	-
Methyl-2-Propen-L-Ol	-	Mil-L-15016	-
Methyl-3-Penten-1-One	F	Mil-L-17331	-
Methyl-4-Isopropyl Benzene	X	Mil-L-2104	-
Methyl-Iso-Amyl-Ketone	F	Mil-L-21260	-
Methyl-L-Propanol	E	Mil-L-23699	-
Methylallyl Acetate	G	Mil-L-25681	-
Methylamyl Alcohol	G	Mil-L-3150	-
Methylcyclohexane	X	Mil-L-4343	-
Methylene Bromide	F	Mil-L-6082	-
Methylene Chloride	F	Mil-L-6085	-
Methylethyl Ketone	E	Mil-L-7808	-
Methylhexyl Ketone	F	Mil-L-7870	-
Methylisobutyl Carbinol	G	Mil-L-9000	-
Methylisobutyl Ketone	G	Mil-L-9236	-
Methylisopropyl Ketone	G	Mil-P-27402	-
Methylactonitrile	E	Mil-R-25576 (RP-1)	-
Methylphenol	G	Mil-S-3136 Type 1 Fuel	-
Methylpropyl Carbinol	E	Mil-S-3136 Type 2 Fuel	-
Methylpropyl Ketone	G	Mil-S-3136 Type 3 Fuel	-
Mil-A-6091	-	Mil-S-3136 Type 4 Oil, Low Swell	-
Mil-C-4339	-	Mil-S-3136 Type 5 Oil, Med Swell	-
Mil-C-7024	-	Mil-S-3136 Type 6 Oil, Hi. Swell	-
Mil-E-9500	-	Mil-S-81087	-
Mil-F-16884	-	Mineral Oil	F
Mil-F-17111	-	Mineral Spirits	F
Mil-F-25558 (Rj-1)	-	Mobile HFA	X
Mil-G-10924	-	Molten Sulfur	G
Mil-G-25013	-	Mono-Chloroacetic Acid	E
Mil-G-25537	-	Monobutyl Ether	G
Mil-G-3545	-	Monochlorobenzene	X
Mil-G-5572	-	Monochlorodifluoromethane	G
Mil-G-7711	-	Monoethanol Amine	E
Mil-H-05606 (HFA)	-	Monoethyl Amine	E
Mil-H-13910	-	Monoethylamine	E
Mil-H-19457	-	Morpholine	E
Mil-H-22251	-	Motor Oil, 40W	C
Mil-H-27601	-	MTBE	G
Mil-H-5606 (j43)	-	Muriatic Acid	E
Mil-H-6083	-	N-Butanal	E
Mil-H-8446 (MLO-8515)	-	N-Butylamine	E
Mil-J-5161	-	N-Butylbenzene	X



## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
N-Butylbromide	F
N-Butylbutyrate	G
N-Butylcarbinol	E
N-Nonyl Alcohol	G
N-Octane	X
N-Serv (75% Xylene)	X
Na-K	-
Naphtha	X
Naphthalene	F
Naphthenic Acids	F
Natural Gas	G
Neohexane	C
Neon Gas	E
Neu-Tri	-
Nickel Acetate	E
Nickel Chloride	E
Nickel Nitrate	E
Nickel Sulfate	E
Nietylene	-
Nitric Acid, 10%	E
Nitric Acid, 13n	X
Nitric Acid, 13n + 5%	X
Nitric Acid, 20%	E
Nitric Acid, 30%	G
Nitric Acid, 30%-70%	F
Nitric Acid, Conc (16n)	X
Nitric Acid, Red Fuming	X
Nitrilotriethanol	E
Nitrobenzene	X
Nitroethane	E
Nitrogen	E
Nitromethane	E
Nitrous Oxide Gas	E
Nonanoic Acid	G
Nonanol	G
Nuto H	-
Nyvac Light	-
Octanoic Acid	G
Octanol	G
Octyl Acetate	G
Octyl Alcohol	G
Octyl Aldehyde	G

CHEMICAL	RATING
Octyl Amine	G
Octyl Carbinol	G
Octylene Glycol	G
Oil-Petroleum	X
Oleic Acid	F
Oleum (Fuming Sulfuric Acid)	X
Olive Oil	G
Orth-Dichlorobenzene	F
Ortho-Dichlorobenzol	F
Orthoxylene	X
Oxalic Acid	E
Oxydiethanol	E
Ozone	E
P-Cymene	X
Paint Thinner	X
Palmatic Acid	E
Papermakers Alum	E
Para-Dichlorobenzene	F
Paraffin Wax	G
Paraldehyde	G
Paraxylene	X
PCB	X
Pelargonic Alcohol	G
Pentachloroethane	X
Pentadione	F
Pentamethylene	F
Pentane	F
Pentanol	G
Pentanone	F
Pentasol	-
Pentyl Acetate	G
Pentyl Alcohol	G
Pental Bromide	F
Pentyl Chloride	F
Pentyl Ether	G
Pentylamine	E
Perchloric Acid-2N	E
Perchloroethylene	X
Perchloromethane	X
Petroleum Crude	X
Petroleum Ether	X
Petroleum Oils	X

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Phenbo	-
Phenol	F
Phenolsulfonic Acid	X
Phenylamine	E
Phenylbromide	X
Phenylbutane	X
Phenylchloride	X
Phenylethylene	X
Phenylmethane	X
Phenylmethanol	G
Phenylmethyl Acetate	C
Phosphate Esters	E
Phosphoric Acid 10%	E
Phosphoric Acid 10%-85%	E
Phosphorus Trichloride	G
Picric Acid, h2O Solution	E
Pine Oil	X
Pinene	X
Poly Chlorinated Biphenol	X
Polyethylene Glycol E-400	E
Polyol Ester	F
Polypropylene Glycol	E
Potassium Acetate	E
Potassium Bisulfate	E
Potassium Bisulfite	E
Potassium Carbonate	E
Potassium Chloride	E
Potassium Chromate	E
Potassium Cyanide	E
Potassium Dichromate	E
Potassium Hydrate	E
Potassium Hydroxide	E
Potassium Nitrate	E
Potassium Permanganate, 5%	E
Potassium Silicate	E
Potassium Sulfate	E
Potassium Sulfide	E
Propanetriol	E
Propanol	E
Propanolamine	E
Propanone	G
Propen-L-ol	E

CHEMICAL	RATING
Propenediamene	E
Propenenitrile	E
Propenyl Alcohol	E
Propenylanisole	F
Propionic Acid	E
Propyl Acetate	E
Propyl Alcohol	E
Propyl Aldehyde	E
Propyl Benzene	X
Propyl Chloride	F
Propyl Ether	G
Propyl Nitrate	G
Propylene	X
Propylene Diamine	G
Propylene Glycol	E
Pydraul, 'E' Series	-
Pydraulic 'C'	-
Quintoluoric B22 Series	-
Red Oil	-
Refrigerant 11	X
Refrigerant 12	X
Refrigerant 22	X
Resorcinol	E
Sae No.10 Oil	C
Sal Ammoniac	E
Sea Water	E
Sewage	E
Silicate Esters	E
Silicate of Soda	E
Silicone Grease	E
Silicone Oil	E
Silver Nitrate	E
Skidrol 500 Type 2	E
Skidrol 500b	E
Skidrol 500c	E
Skidrol 7000 Type 2	E
Soap Solutions	E
Soda Ash	E
Soda Lime	E
Soda Niter	E
Soda, Caustic	E
Sodium Acetate	E

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Sodium Aluminate	E
Sodium Bicarbonate	E
Sodium Dichromate	E
Sodium Hydrate	E
Sodium Hydrochlorite	G
Sodium Hydroxide (Caustic Soda)	E
Sodium Hypochlorite	C
Sodium Metaphosphate	E
Sodium Nitrate	E
Sodium Perborate	E
Sodium Peroxide	E
Sodium Phosphate	E
Sodium Silicate	E
Sodium Sulfate	E
Sodium Sulfide	E
Sodium Sulfite	E
Sodium Thiosulfate	E
Soybean Oil	G
Stannic Chloride	E
Stannic Sulfide	E
Stannous Chloride	E
Stannous Sulfide	E
Steam, below 350 F	X
Stearic Acid	E
Stoddart Solvent	F
Styrene	X
Sulfamic Acid	E
Sulfur	F
Sulfur Chloride	G
Sulfur Dioxide	E
Sulfur Trioxide, Dry	E
Sulfuric Acid 60% (200 F)	E
Sulfuric Acid, 25%	E
Sulfuric Acid, 25%-50%	G
Sulfuric Acid, 50%-96%	F
Sulfuric Acid, Conc.	X
Sulfuric Acid, Fuming	X
Sulfurous Acid, 10%	E
Sulfurous Acid, 10%-85%	E
Sutan	-
T-Butyl Amine	G
Tall Oil	F

CHEMICAL	RATING
Tallow	G
Tannic Acid	E
Tar	X
Tar Bituminous	X
Tartaric Acid	E
Telone 2	-
Terpinol	G
Tertiary Butyl Alcohol	E
Tertiary Butyl Amine	E
Tetrachloromethane	X
Tetrachloronaphthalene	X
Tetraethylene Glycol	G
Tetraethylorthosilicate	G
Tetrahydrofuran	F
Thf	F
Tine Chloride	E
Titanium Tetrachloride	G
Toluene	X
Toluidine	X
Toluol	X
Transformer Oil	X
Transmission 'A' Oil	X
Tri (2-Hydroxyethyl) Amine	F
Tributyl Phosphate	E
Tributylamine	G
Trichloroacetic Acid	E
Trichlorobenzene	X
Trichloroethane	G
Trichloroethylene	G
Trichloromethane	X
Trichlorotoluene	X
Tricresyl Phosphate	E
Triethanolamine	E
Triethylamine	E
Triethylene Glycol	E
Trihydroxybenzoic Acid	E
Trimethyl Pentanes (Mixed)	X
Trimethyl Pentene	X
Trimethylamine	E
Trisodium Phosphate	E
Tritoyl Phosphate	G
Tung Oil	C

## RESISTANCE RATINGS

Resistant	R	Not Resistant	NR	Testing Needed	T
-----------	---	---------------	----	----------------	---

CHEMICAL	RATING
Tung Oil (China Oil)	C
Turpentine	X
Udmh	-
Undecyl Alcohol	F
Urea	E
Urethane Formulations	G
Uric Acid	E
Varnish	X
Vegetable Oils	G
Versilibe f44	-
Versilubr f55	-
Vinegar	E
Vinegar Acid	E
Vinyl Acetate	E
Vinyl Benzene	X
Vinyl Chloride	G
Vm & Naphtha	-
Water	E
Water, Boiling	E
Water, Soda	E
Wemco C	-
Whisky	E
White Oil	X
White Pine Oil	X
Wines	E
Wood Alcohol	E
Wood Oil	G
Xenon	E
Xylene, Xylon	X
Xylidine	-
Zeolites	E
Zinc Carbonate	E
Zinc Chloride	E
Zinc Chromate	E
Zinc Sulfate	E
Zinc, Acetate	E
0-Aminotoluene	F
1-Undecanol	F
1,4-Dioxane	E
1-Amino 2 Propanol	E
1-Aminobutane	E
1-Aminopentane	G

CHEMICAL	RATING
1-Bromo-3-Methyl Propane	F
1-Bromo-3-Methyl Butane	F
1-Bromobutane	F
1-Chloro-2-Methyl Propane	F
1-Chloro-3-Methyl Butane	F
1-Decanol	G
1-Hendacanol	F
2 (2 Aminoethylamino) Ethanol	E
2 (2 Ethoxyethoxy) Ethanol	E
2 (2 Ethoxyethoxy) Ethyl Acetate	E
2, 4-Di-Sec-Pentylphenol	F
2-Aminoethanol	E
2-Chloro-1-Hydroxy-Benzene	F
2-Chlorophenol	F
2-Chloropropane	G
2-Ethoxyethanol	E
2-Ethoxyethyl Acetate	E
2-Ethyl (Butyraldehyde)	G
2-Ethyl-1-Hexanol	E
2-Ethylhexanoic Acid	G
2-Ethylhexyl Acetate	G
2-Octanone	F
3-Bromopropene	F
3-Chloro-2-Methyl Propane	F
3-Chloropropene	F
30Al Oil	-
4-Hydroxy-4-Methyl-2-Pentanone	F